## **TOLERANCES**

## **CF CARBON BARS**

**Cold Drawn or Turned & Polished** 

-	Undersize Variations in Inches				
Size Range in Inches	Max. Carbon Range .28% or less	Max. Carbon Range Over .28% to .55% incl.	Max. Carbon Range to 0.55% incl. Stress Relieved or Annealed After Cold Finishing	Max. Carbon Range Over 55% or all Grades Quenched & Tempered or Normal- ized and Tempered Before Cold Finishing	
1½ or under	.002	.003	.004	.005	
Over $1\frac{1}{2}$ to $2\frac{1}{2}$ , incl.	.003	.004	.005	.006	
Over $2\frac{1}{2}$ to 4, incl.	.004	.005	.006	.007	
Over 4 to 6, incl.	.005	.006	.007	.008	
Over 6 to 8, incl.	.006	.007	.008	.009	
Over 8 to 9, incl.	.007	.008	.009	.010	
Over 9.008	.009	.010	.011		
COLD DRAWN HEXAGONS					
¾ or under	.002	.003	.004	.006	
Over $\frac{3}{4}$ to $1\frac{1}{2}$ , incl.	.003	.004	.005	.007	
Over $1\frac{1}{2}$ to $2\frac{1}{2}$ , incl.	.004	.005	.006	.008	
Over 2½ to 3½, incl.	.005	.006	.007	.009	
Over 3½ to 4, incl.	.005	.006			
COLD DRAWN SQUARES					
3/4 or under	.002	.004	.005	.007	
Over $\frac{3}{4}$ to $1\frac{1}{2}$ , incl.	.003	.005	.006	.008	
Over $1\frac{1}{2}$ to $2\frac{1}{2}$ , incl.	.004	.006	.007	.009	
Over $2\frac{1}{2}$ to 4, incl.	.006	.008	.009	.011	
Over 4 to 5, incl.	.010	_	_	_	
Over 5 to 6, incl.	.014		<u> </u>		
COLD DRAWN FLATS Tolerances for flats apply to thickness as well as width					
Width in Inches					
To ¾, incl.	.003	.004	.006	.008	
Over $\frac{3}{4}$ to $\frac{1}{2}$ , incl.	.004	.005	.008	.010	
Over $1\frac{1}{2}$ to 3, incl.	.005	.006	.010	.012	
Over 3 to 4, incl.	.006	.008	.011	.016	
Over 4 to 6, incl.	.008	.010	.012	.020	
Over 6.013	.015	_	_		
TIPLED COOLING AND DOLLARS TO THE TOTAL OF T					

## TURNED, GROUND AND POLISHED ROUNDS COLD DRAWN, GROUND AND POLISHED ROUNDS

Size	Undersize Variations in Inches			
Range in Inches	Turned, Ground and Polished Rounds	Cold Drawn, Ground and Polished Rounds		
1½ and under	0005 to0015	.001		
Over $1\frac{1}{2}$ to less than $2\frac{1}{2}$	0005 to0020	.0015		
$2\frac{1}{2}$ to 3, incl.	0005 to0025	.002		
Over 3 to 4, incl.	0005 to0035	.003		
Over 4 to 6, incl.	0005 to0045	.004		
Over 60005 to0055	.005			

<sup>\*</sup>All tolerances are on the minus side, +.000.

For nonresulphurized steels (steels specified to maximum sulphur limits under 0.08%) or for steels thermally treated, the tolerance is increased by .001".

